

Technical Product Data Sheet

Intertape® 4118



Intertape® 4118 is a Kapton® polyimide film electrical adhesive tape. Kapton® polyimide backing and silicone adhesive offers outstanding thermal resistance and excellent electrical insulating properties. This tape is used where toughness, Puncture resistance, extreme resistance to heat, and flame retardance are required. MeasuRed (19) against maximum temperature criteria (VDE 03340, DIN 40633) this tape can withstand high temperatures for limited periods of time (250°C = 1.000 hours, 350°C = 10 hours). Flame retardant according to UL510.

Nominal Values

Backing Kapton®, Polyimide Film

Backing Thickness 0,025 mm

Adhesive Type | Silicone, thermosetting

Total Thickness 0,069 mm

Insulation Class H 180°C (DIN EN 60085, OANZ2 & OANZ8)

Color Amber (00)

Adhesion to Steel 6,80 N/25 mm

Tensile Strength 130,00 N/25 mm

Elongation at Break 60%

Insulation Resistance (mega Ω) | $10^6\Omega$

Electrolytic Corrosion A1,0

Flammability BU1

UL-File # | E20780

Length 33 m, other lengths upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, other

widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 04 December 2019















DE-79227 Schallstadt



Technical Product Data Sheet

Intertape® 4118



Applications

- Core and inter-layer insulation in tranformers
- protection of gold plated contacts on PC-boards during wave-soldering and where residue free removal of the tape is required
- Ground barrier and phase insulation in high performance coils
- Outer wrap on small bobbin wound coils
- Form wound coils for traction motors
- Final bandaging of coils
- Taping of coreless coils
- Contact protection against current carrying conductors

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 18°C to 24°C, with a relative humidity of 40% to 50%. When using an adhesive tape stored below 18°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 17.11.2025





We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of







