

Technical Product Data Sheet

Intertape® 4560



Intertape® 4560 features an absorbent, silk acetate cloth backing with a thermosetting, rubber adhesive. The tape is resistant to impregnating agents, can be printed on directly, and can be torn by hand.

Nominal Values

Backing Silk Acetate Cloth

Backing Thickness 0,152 mm

> **Adhesive Type** Natural Rubber, thermosetting

Total Thickness 0,178 mm

Insulation Class B 130°C (DIN EN 60085, OANZ2 & OANZ8)

> Color White (08), Black (04)

Adhesion to Steel 15,00 N/25 mm

Tensile Strength 175,00 N/25 mm

Elongation at Break 15%

Dielectric Strength 2000 V

Insulation Resistance (megaΩ) $10^4\Omega$

> **Electrolytic Corrosion** A1,0

> > **Flammability** BU1

> > > **UL-File #** E20780

Length 50 m, other lengths upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, other

widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 02 May 2022





DE-79227 Schallstadt



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the









Technical Product Data Sheet

Intertape® 4560



Applications

- Coil wrapping
- Tabbing
- Inter-layer insulation

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 18°C to 24°C, with a relative humidity of 40% to 50%. When using an adhesive tape stored below 18°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 04.11.2025







We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the







