

Intertape® 51245



Intertape® 51245 is a multi-purpose tape for applications which require a combination of tear and Puncture resistance, high tensile strength with elongation, and excellent dielectric strength. The combination of PET Film and polyester non-woven materials can be used on a wide variety of electrical applications.

Nominal Values

Backing	PET Laminate, PET Film / PET Non-Woven
Backing Thickness	0,089 mm
Adhesive Type	Natural Rubber, thermosetting
Total Thickness	0,134 mm
Insulation Class	B 130°C (DIN EN 60085, OANZ2 & OANZ8)
Color	White (08)
Adhesion to Steel	23,25 N/25 mm
Tensile Strength	136,00 N/25 mm
Elongation at Break	50%
Dielectric Strength	5000 V
Insulation Resistance (megaΩ)	10 ⁵ Ω
Electrolytic Corrosion	A1,0
Flammability	BU2
UL-File #	E20780
Length	66 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 75 mm, 1000 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	02 May 2022

Intertape® 51245



Applications

- High volume coil wrapping Applications
- Ground and barrier insulation
- Outer protective wrap for bobbin applications
- Coil end insulation anchoring leads
- Terminal board pads

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 18°C to 24°C, with a relative humidity of 40% to 50%. When using an adhesive tape stored below 18°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 29.08.2025