

## Intertape® 51578



Intertape® 51578 is an electrical insulation tape with a combined backing of PET Film, paper fleece and a thermosetting, rubber adhesive compound. It is resistant to light and aging, has high adhesive strength, is impregnant-neutral, free of corrosion-promoting components, and it is UL-listed.

## Nominal Values

<b>Backing</b>	PET Laminate, PET Film / Paper-Non-Woven
<b>Backing Thickness</b>	0,089 mm
<b>Adhesive Type</b>	Natural Rubber, thermosetting
<b>Total Thickness</b>	0,140 mm
<b>Insulation Class</b>	B 130°C (DIN EN 60085, OANZ2 & OANZ8)
<b>Color</b>	White (08)
<b>Adhesion to Steel</b>	19,00 N/25 mm
<b>Tensile Strength</b>	175,00 N/25 mm
<b>Elongation at Break</b>	2%
<b>Dielectric Strength</b>	4500 V
<b>Insulation Resistance (megaΩ)</b>	10 <sup>4</sup> Ω
<b>Electrolytic Corrosion</b>	A1,0
<b>Flammability</b>	BU3
<b>UL-File #</b>	E20780
<b>CSA-File #</b>	LR94980
<b>Length</b>	55 m, other lengths upon request
<b>Width</b>	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, other widths upon request
<b>Storage Life</b>	The material can be stored at room temperature for at least 12 months.
<b>Effective</b>	02 May 2022

# Intertape® 51578



## Applications

- Slot edging
- Lead anchoring
- Coil wrapping
- Harness
- Inter-phase/Inter-layer insulation

## Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 18°C to 24°C, with a relative humidity of 40% to 50%. When using an adhesive tape stored below 18°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 08.01.2026