

Intertape® 6130



Intertape® 6130 has a PET Film backing with a silicone adhesive. It provides flexibility, solvent-resistance, puncture-resistance, high chemical-resistance, and excellent long-term aging characteristics. It also provides a secure seal without leakage and it removes without residues.

Nominal Values

Backing	PET Film
Backing Thickness	0,025 mm
Adhesive Type	Silicone
Total Thickness	0,066 mm
Color	Red (19)
Adhesion to Steel (N/25mm)	8,75 N/25 mm
Tensile Strength	114,00 N/25 mm
Elongation at Break	120%
Temperature Resistance	+204°C
Length	66 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	15 February 2022

Intertape® 6130



Applications

- Protects printed circuitry from plating solutions Fumes without contaminating bath solutions such as those used in tin/lead stripping and 'gold finger' plating operations
- For splicing of release-coated paper and film stocks

Benefits

- Suitable for High Temperatures

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 18°C to 24°C, with a relative humidity of 40% to 50%. When using an adhesive tape stored below 18°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 25.04.2024