IPG® (Intertape®) 4560



IPG® (Intertape®) 4560 features an absorbent, silk acetate cloth backing with a thermosetting, rubber adhesive. The tape is resistant to impregnating agents, can be printed on directly, and can be torn by hand.

Nominal Values

Backing	Silk Acetate Cloth
Backing Thickness	0,152 mm
Adhesive Type	Natural Rubber, thermosetting
Total Thickness	0,178 mm
Insulation Class	B 130°C (DIN EN 60085, OANZ2 & OANZ8)
Color	White (08), Black (04)
Adhesion to Steel	15,00 N/25 mm
Tensile Strength	175,00 N/25 mm
Elongation at Break	15%
Dielectric Strength	2000 V
Insulation Resistance (megaΩ)	$10^4\Omega$
Electrolytic Corrosion	A1,0
Flammability	BU1
UL-File #	E20780
Length	50 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	02 May 2022

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

IPG® (Intertape®) 4560



Applications

- Coil wrapping
- Tabbing
- Inter-layer insulation

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 18°C to 24°C, with a relative humidity of 40% to 50%. When using an adhesive tape stored below 18°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 22.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com