



## IPG® (Intertape®) 51597

IPG® (Intertape®) 51597 is a PET Film / Glass Filament Reinforced Electrical Tape. High tensile strength, conformable backing and aggressive for a large variety of insulating and holding applications. This tape is resistant to chemicals, solvents, and aging and offers a high dielectric strength and insulation resistance.

### Nominal Values

<b>Backing</b>	PET Laminate, PET Film, Glass Filament
<b>Backing Thickness</b>	0,140 mm
<b>Adhesive Type</b>	Acrylic
<b>Total Thickness</b>	0,165 mm
<b>Insulation Class</b>	F 155°C (DIN EN 60085, OANZ2 & OANZ8)
<b>Color</b>	Clear (00)
<b>Adhesion to Steel</b>	11,00 N/25 mm
<b>Tensile Strength</b>	1095,00 N/25 mm
<b>Elongation at Break</b>	5%
<b>Dielectric Strength</b>	5000 V
<b>Insulation Resistance (megaΩ)</b>	10 <sup>4</sup> Ω
<b>Electrolytic Corrosion</b>	A1,0
<b>Flammability</b>	BU2
<b>UL-File #</b>	E20780
<b>CSA-File #</b>	LR94980
<b>Length</b>	66 m, other lengths upon request
<b>Width</b>	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, other widths upon request
<b>Storage Life</b>	The material can be stored at room temperature for at least 12 months.
<b>Effective</b>	02 May 2022

## IPG® (Intertape®) 51597



### Applications

- Slot edging
- Holding and separating ground insulation
- Bundling motor and transformer coils

### Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 21.04.2026