

## IPG® (Intertape®) 6130



IPG® (Intertape®) 6130 has a PET Film backing with a silicone adhesive. It provides flexibility, solvent-resistance, puncture-resistance, high chemical-resistance, and excellent long-term aging characteristics. It also provides a secure seal without leakage and it removes without residues.

### Nominal Values

<b>Backing</b>	PET Film
<b>Backing Thickness</b>	0,025 mm
<b>Adhesive Type</b>	Silicone
<b>Total Thickness</b>	0,066 mm
<b>Color</b>	Red (19)
<b>Adhesion to Steel</b>	8,75 N/25 mm
<b>Tensile Strength</b>	114,00 N/25 mm
<b>Elongation at Break</b>	120%
<b>Temperature Resistance</b>	+204°C
<b>Length</b>	66 m, other lengths upon request
<b>Width</b>	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, other widths upon request
<b>Storage Life</b>	The material can be stored at room temperature for at least 12 months.
<b>Effective</b>	15 February 2022

## IPG® (Intertape®) 6130



### Applications

- Protects printed circuitry from plating solutions Fumes without contaminating bath solutions such as those used in tin/lead stripping and 'gold finger' plating operations
- For splicing of release-coated paper and film stocks

### Benefits

- Suitable for High Temperatures

### Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 18°C to 24°C, with a relative humidity of 40% to 50%. When using an adhesive tape stored below 18°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 15.06.2026