

## IPG® (Intertape®) PE8



IPG® (Intertape®) PE8 is a durable, moisture resistant PE (polyethylene) film backing with a synthetic rubber-based pressure-sensitive adhesive designed to offer high conformability without excessive stretch. Bonds well to a variety of surfaces. Clean removal from a variety of gel-coated surfaces.

### Nominal Values

<b>Backing</b>	PE Film
<b>Adhesive Type</b>	Synthetic Rubber
<b>Total Thickness</b>	0,230 mm
<b>Color</b>	White (08)
<b>Adhesion to Steel</b>	24,60 N/25 mm
<b>Tensile Strength</b>	100,70 N/25 mm
<b>Temperature Resistance</b>	+7°C to +93°C
<b>Length</b>	33 m, Other lengths and spools upon request
<b>Width</b>	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1440 mm, other widths upon request
<b>Storage Life</b>	The material can be stored at room temperature for at least 12 months.
<b>Effective</b>	27 November 2019

# IPG<sup>®</sup> (Intertape<sup>®</sup>) PE8



## Applications

- For patching and repairs, bundling and wrapping
- Sealing, and separation of dissimilar metals
- Color coding and identification
- Seaming or sealing PE films used for marine and transportation preservation

## Benefits

- High degree of conformability without excessive stretch
- Easy to handle due to stiff backing
- Moisture resistant
- Durable
- Bonds well to a variety of surfaces
- UV resistance up to six months, depending upon conditions and surfaces

## Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 18°C to 24°C, with a relative humidity of 40% to 50%. When using an adhesive tape stored below 18°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 20.04.2026