



## IPG® (Intertape®) PE9

IPG® (Intertape®) PE9 is a durable, moisture resistant PE (polyethylene) film backing with a synthetic rubber-based pressure-sensitive adhesive designed to offer high conformability without excessive stretch. Bonds well to a variety of surfaces.

### Nominal Values

|                               |   |
|-------------------------------|---|
| <b>Backing</b>                | PE Film   |
| <b>Adhesive Type</b>          | Synthetic Rubber  |
| <b>Total Thickness</b>        | 0,230 mm  |
| <b>Color</b>                  | White (08)  |
| <b>Adhesion to Steel</b>      | 26,00 N/25 mm   |
| <b>Tensile Strength</b>       | 109,50 N/25 mm  |
| <b>Elongation at Break</b>    | 110%  |
| <b>Temperature Resistance</b> | +7°C to +93°C   |
| <b>Length</b>                 | 55 m, Other lengths and spools upon request   |
| <b>Width</b>                  | 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1440 mm, other widths upon request |
| <b>Storage Life</b>           | The material can be stored at room temperature for at least 12 months.                          |
| <b>Effective</b>              | 27 November 2019  |

## IPG® (Intertape®) PE9



### Applications

- For patching and repairs, bundling and wrapping
- Sealing, and separation of dissimilar metals
- Color coding and identification
- Used for marine shrink wrap applications and vapor barrier seaming

### Benefits

- High degree of conformability without excessive stretch
- Easy to handle due to stiff backing
- Moisture resistant
- Durable
- Bonds well to a variety of surfaces

### Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 18°C to 24°C, with a relative humidity of 40% to 50%. When using an adhesive tape stored below 18°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 04.03.2026