



## Saint-Gobain / h-old® H20

Saint-Gobain / h-old® H20 is a Kapton® film coated on one side with high quality pressure sensitive silicone adhesive. Designed for high temperature electrical applications where a thin, conformable backing combined with excellent dielectrical properties are required. NuClear (00) radiations resistant. Flame retardant UL 510.

### Nominal Values

<b>Manufacturer</b>	Saint-Gobain / h-old®
<b>Backing</b>	Kapton® Film, Polyimide Film
<b>Backing Thickness</b>	0,025 mm
<b>Adhesive Type</b>	Silicone
<b>Total Thickness</b>	0,060 mm
<b>Insulation Class</b>	H 180°C (DIN EN 60085, OANZ2 & OANZ8)
<b>Color</b>	Brown (79), Green (37), (Green by request -not UL-listed)
<b>Adhesion to Steel</b>	5,75 N/25 mm
<b>Tensile Strength</b>	112,50 N/25 mm
<b>Elongation at Break</b>	35%
<b>Breakdown Voltage</b>	6500 V
<b>Electrolytic Corrosion</b>	1
<b>Rolling Ball Tack</b>	< 10 cm
<b>Temperature Resistance</b>	+260°C, (short-term)
<b>UL-File #</b>	E178430
<b>Length</b>	33 m, other lengths upon request
<b>Width</b>	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 660 mm, other widths upon request
<b>Storage Life</b>	The material can be stored at room temperature for at least 12 months.
<b>Effective</b>	29 March 2021

## Saint-Gobain / h-old® H20



### Applications

- Insulation of bobbins, transformers, motors, capacitors, wire harnesses
- Printed circuit board assembly
- High temperature masking operations

### Benefits

- Very high temperature resistance
- Flame retardant UL 510
- Good chemical and solvent resistance

### Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 23.11.2024