



Saint-Gobain / h-old® P34-00

Saint-Gobain / h-old® P34-00 is PET Film coated with high quality acrylic adhesive. It is designed for coil wrapping, inter-layer insulation, anchoring, holding, harnessing, splicing, etc.

Nominal Values

Manufacturer	Saint-Gobain / h-old®
Backing	PET Film
Backing Thickness	0,023 mm
Adhesive Type	Acrylic
Total Thickness	0,060 mm
Insulation Class	B 130°C (DIN EN 60085, OANZ2 & OANZ8)
Color	Clear (00)
Adhesion to Steel	8,75 N/25 mm
Tensile Strength	100,00 N/25 mm
Elongation at Break	80%
Breakdown Voltage	4500 V
Temperature Resistance	+180°C, (short-term)
UL-File #	E178430
Length	66 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1280 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	29 March 2021

Saint-Gobain / h-old® P34-00



Applications

- Coil wrapping
- Interlayer insulation coil wrapping, inter-layer insulation, anchoring, holding, harnessing, splicing, etc.
- Motor & transformer manufacturers
- Capacitor manufacturers
- Splicing of papers and films
- Identification

Benefits

- Good adhesion and initial tack
- High conformability and chemical resistance
- Excellent flagging and solvent resistance

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 16.07.2024