Saint-Gobain / h-old® P34-00



Saint-Gobain / h-old® P34-00 is PET Film coated with high quality acrylic adhesive. It is designed for coil wrapping, inter-layer insulation, anchoring, holding, harnessing, splicing, etc.

Nominal Values

Backing	PET Film
Backing Thickness	0,023 mm
Adhesive Type	Acrylic
Total Thickness	0,060 mm
Insulation Class	B 130°C (DIN EN 60085, OANZ2 & OANZ8)
Color	Clear (00)
Adhesion to Steel	8,75 N/25 mm
Tensile Strength	100,00 N/25 mm
Elongation at Break	80%
Dielectric Strength	4500 V
Temperature Resistance	+180°C, (short-term)
UL-File #	E178430
Length	66 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1280 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	29 March 2021

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

Saint-Gobain / h-old® P34-00



Applications

- Coil wrapping
- Interlayer insulation coil wrapping, inter-layer insulation, anchoring, holding, harnessing, splicing, etc.
- Motor & transformer manufacturers
- Capacitor manufacturers
- Splicing of papers and films
- Identification

Benefits

- Good adhesion and initial tack
- High conformability and chemical resistance
- Excellent flagging and solvent resistance

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 04.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com