

Saint-Gobain / h-old® PR25



Saint-Gobain / h-old® PR25 is a glass filament reinforced PET film coated on one side with a rubber thermosetting adhesive system. Designed for holding applications where a high tensile strength, good initial tack and thermal resistance are required.

Nominal Values

| | |
|-------------------------------|---|
| Backing | PET Film, Glass Filament |
| Backing Thickness | 0,085 mm |
| Adhesive Type | Natural Rubber, thermosetting |
| Total Thickness | 0,120 mm |
| Insulation Class | B 130°C (DIN EN 60085, OANZ2 & OANZ8) |
| Color | White (08) |
| Adhesion to Steel | 8,75 N/25 mm, 6,25 N/25 mm (90°) |
| Tensile Strength | 950,00 N/25 mm |
| Elongation at Break | 5% |
| Dielectric Strength | 5000 V |
| Electrolytic Corrosion | 1 |
| Rolling Ball Tack | < 10 cm |
| Temperature Resistance | +160°C, (short-term) |
| UL-File # | E178430 |
| Length | 50 m, other lengths upon request |
| Width | 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1000 mm, other widths upon request |
| Storage Life | The material can be stored at room temperature for at least 12 months. |
| Effective | 29 March 2021 |

Saint-Gobain / h-old® PR25



Applications

- Insulation of electrical motors, generators, etc.
- Outer wrapping, tabbing and anchoring leads of electrical transformers, coils, etc.

Benefits

- Good thermal and puncture resistance
- High chemical resistance when thermoset

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 13.12.2025