

Technical Product Data Sheet

Saint-Gobain / h-old® PVX30



Saint-Gobain / h-old® PVX30 is a glass filament reinforced PET Film coated on one side with a high quality acrylic adhesive system. Designed for holding applications where a high tensile strength combined with a good thermal and chemical resistance are required.

Nominal Values

Backing PET Film, Glass Filament

Backing Thickness 0,110 mm

Adhesive Type | modified, Acrylic

Total Thickness 0,175 mm

Insulation Class F 155°C (DIN EN 60085, OANZ2 & OANZ8)

Color Clear (00)

Adhesion to Steel 15,00 N/25 mm, 9,50 N/25 mm (90°)

Tensile Strength 950,00 N/25 mm

Elongation at Break 4%

Dielectric Strength 5000 V

Electrolytic Corrosion | 1

Rolling Ball Tack < 10 cm

Temperature Resistance +180°C, (short-term)

UL-File # | E178430

Length 50 m, other lengths upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 980

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 29 March 2021















DE-79227 Schallstadt



Technical Product Data Sheet

Saint-Gobain / h-old® PVX30



Applications

- Used for heavy-duty holding, banding, bundling, anchoring and reinforcing functions
- Outer wrapping, tabbing and anchoring leads of electrical transformers, coils, etc.

Benefits

- Good thermal resistance
- Outstanding tensile strength
- High resistance to solvents, oils and chemicals

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 04.11.2025





DE-79227 Schallstadt

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the







standard processing guidelines for adhesive tapes, which we will gladly send you upon request.