Saint-Gobain / h-old® PVX30



Saint-Gobain / h-old® PVX30 is a glass filament reinforced PET Film coated on one side with a high quality acrylic adhesive system. Designed for holding applications where a high tensile strength combined with a good thermal and chemical resistance are required.

Nominal Values

Backing	PET Film, Glass Filament
Backing Thickness	0,110 mm
Adhesive Type	modified, Acrylic
Total Thickness	0,175 mm
Insulation Class	F 155°C (DIN EN 60085, OANZ2 & OANZ8)
Color	Clear (00)
Adhesion to Steel	15,00 N/25 mm, 9,50 N/25 mm (90°)
Tensile Strength	950,00 N/25 mm
Elongation at Break	4%
Dielectric Strength	5000 V
Electrolytic Corrosion	1
Rolling Ball Tack	< 10 cm
Temperature Resistance	+180°C, (short-term)
UL-File #	E178430
Length	50 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 980 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	29 March 2021

VOLZ TAPES

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

Saint-Gobain / h-old® PVX30



Applications

- Used for heavy-duty holding, banding, bundling, anchoring and reinforcing functions
- Outer wrapping, tabbing and anchoring leads of electrical transformers, coils, etc.

Benefits

- Good thermal resistance
- Outstanding tensile strength
- High resistance to solvents, oils and chemicals

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 10.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com