

Technical Product Data Sheet

tesa® 58372



tesa® 58372 is a translucent, double-sided PET tape equipped with flame retardant tackified acrylic adhesive. The flame retardant acrylic adhesive gives this product unique anti-flaming property, and also a good bonding performance even after long-term storage conditions. Its ultra thin PET backing offers excellent converting performance for purpose of lamination. The white/red logo glassine liner ensures it can be easily released without adhesive residue.

Nominal Values

Manufacturer tesa®

> **Backing** PET Film

Backing Thickness 0,069 mm

> **Adhesive Type** modified, flame-retardant, Acrylic

Total Thickness 0,050 mm

> Color Clear (00)

Liner White, siliconized Paper, with red logo

Adhesion to Steel 17,75 N/25 mm

Temperature Resistance +125°C, (long-term)

> Length 100 m, other lengths upon request

6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1250 Width

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 09 August 2021





DE-79227 Schallstadt



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the







Technical Product Data Sheet

tesa® 58372



Applications

• Applied in power battery or any lamination application (heating plate mounting, etc) where additional flame retardant properties are required

Benefits

- Flame retardant per UL94 VTM-0 level
- Good bonding performance
- High long-term reliability and aging resistance
- Good handling performance in converting process
- Conforming to RoHS, REACH
- Halogen-free

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 23.11.2024













DE-79227 Schallstadt