tesa®ACXplus 7055

tesa® ACXplus 7055 is a highly transparent acrylic core tape designed for bonds that achieve a seamless and optical clear finish. Translucent and transparent materials, such as glass or acrylic are easy to bond with tesa® ACXplus 7055.

Nominal Values

Backing	solid Acrylic
Adhesive Type	Acrylic
Total Thickness	1,00 mm
Color	Clear (00)
Liner	Silicone-free film
Adhesion to Steel	60,00 N/25 mm (90°)
Tensile Strength	100 N/cm²
Shear Strength	35 N/cm²
Static Shear	3 cm² / 72 h: 750 g (23°C), 500 g (70°C)
Temperature Resistance	+200°C (short-term), '+110°C (long-term)
Length	25 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 19 mm, 25 mm, 880 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Density	ca. 1030 kg/m3
Effective	30 November 2024

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

TAPES
Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

tesa®ACXplus 7055

Applications

- Bonding transparent / translucent substrates
- Ideal for glass and acrylic substrates
- Extruded profiles
- Signage mounting
- Plisse profiles
- For Indoor and outdoor applications

Benefits

- Highly transparent
- Provides seamless and optical clear finish

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 19°C to 21°C, with a relative humidity of 50%. When using an adhesive tape stored below 19°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 22.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com