

## **Technical Product Data Sheet**

## volzAcrylicFoam 74025 PV1



volzAcrylicFoam 74025 PV1 is based on a clear solid acrylic adhesive. It is stable in both high and low temperatures and is strong under UV. volzAcrylicFoam 74025 PV1 has a high heat, chemical and moisture resistance. Its excellent holding power withstands various weights in many types of environments.

#### **Nominal Values**

Acrylic Foam **Backing** 

**Adhesive Type** Acrylic

**Total Thickness** 0,250 mm

> Color Clear (00)

Liner PE Film, (red)

**Static Shear** 1000 g (+23°C), 500 g (+93°C)

+93°C (long-term - weeks), +150°C (short-term - hours), +120°C melting **Temperature Resistance** 

point

Length 66 m, other lengths upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 930


mm, other widths upon request

**Storage Life** The material can be stored at room temperature for at least 12 months.

**Effective** 27 September 2024







DE-79227 Schallstadt

Phone: +49 (0)7664 50500-0 Fax: +49 (0)7664 50500-50

info@volztapes.com www.volztapes.com



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the











# **Technical Product Data Sheet**

## volzAcrylicFoam 74025 PV1



### **Applications**

- Metal, glass, high surface energy plastics
- Joining clear materials
- Signs and nameplates
- Decoration panels

#### **Benefits**

- No VOC, and environmentally friendly
- Strong under UV
- Excellent holding power
- Stable in low and high temperature Heat, chemical and moisture resistant

#### **Storage Conditions**

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 18.04.2025





We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of









DE-79227 Schallstadt