

volzAcrylicFoam 76080-55 PV1



volzAcrylicFoam 76080-55 PV1 is a high performance, double-sided adhesive tape consisting of an acrylic adhesive coated on a firm acrylic foam carrier. This product was developed for use in the automotive industry, the electrical industry and many other areas of application and offers excellent adhesion to a wide variety of surfaces. The tape is also characterized by its high temperature resistance.

Nominal Values

| | |
|-------------------------------|---|
| Backing | Acrylic Foam |
| Adhesive Type | Acrylic |
| Total Thickness | 0,80 mm (± 10%) |
| Color | Grey (55) |
| Liner | red PE Film |
| Adhesion to Steel | 49,03 N/25 mm |
| Shear Strength | 8 kgf/cm ² |
| Static Shear | 3,23 cm ² /168 h: 1500 g (23°C), 750 g (93°C) |
| Temperature Resistance | +150°C (short-term), +93°C (long-term) |
| Length | 33 m, other lengths upon request |
| Width | 4 mm – 930 mm, other widths upon request |
| Storage Life | The material can be stored at room temperature for at least 12 months. |
| Slitting Tolerance | Length < 33m = ± 0,4mm (± 1/64"), Length > 33m = ± 0,8mm (± 1/32"), Lower tolerances on inquiry and perhaps against extra charge possible, Cross-wound spools are not similar to the above mentioned tolerances |
| Effective | 13 June 2025 |

volzAcrylicFoam 76080-55 PV1



Applications

- Metal, glass, high surface energy plastics
- Automotive
- Construction

Benefits

- Excellent holding power and temperature resistance
- Can withstand extreme weights and heat
- Superb adhesion
- Good UV and chemical resistance

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 21°C to 30°C, with a relative humidity of 50%. When using an adhesive tape stored below 21°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 14.07.2025