

# **Technical Product Data Sheet**

## volzElekto 11203



volzElektro 11203 is a PTFE (polytetrafluoroethylene) film coated with a high-temperature silicone adhesive system. Designed for high temperature insulation, as release wrap on rollers in numerous applications, cure process of composites materials and all applications where a low-friction, anti-stick and non-toxic properties are required.

#### **Nominal Values**

PTFF Film **Backing** 

**Backing Thickness** 0,130 mm

> **Adhesive Type** Silicone

**Total Thickness** 0.190 mm

**Insulation Class** H 180°C (DIN EN 60085, OANZ2 & OANZ8)

> Color Grey (55)

**Adhesion to Steel** 8,75 N/25 mm

**Tensile Strength** 200,00 N/25 mm

**Elongation at Break** 320%

**Dielectric Strength** 11500 V

**Electrolytic Corrosion** 1

> **Rolling Ball Tack** < 10 cm

**Temperature Resistance** 260°C (short-term)

> Length 33 m, other lengths upon request

6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 75 Width

mm, 1000 mm, other widths upon request

**Storage Life** The material can be stored at room temperature for at least 12 months.

**Effective** 14 September 2021





DE-79227 Schallstadt



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the











# **Technical Product Data Sheet**

## volzElekto 11203



### **Applications**

- Used in the manufacture of motors and transformers
- Used in the automotive, aerospace, composite materials and other industries

#### **Benefits**

- Oustanding temperature resistance
- Good chemical resistance
- Low-friction and anti-stick surface

### **Storage Conditions**

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 16.09.2025





We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of









DE-79227 Schallstadt