

Technical Product Data Sheet

volzElektro 1018 PV4



volzElektro 1018 PV4 is a Kapton® CR Film Electrical Tape (Corona resistant) manufactured from Kapton® film with a high-performing, thermosetting, silicone adhesive. volzElektro 1018 PV4 can pRotect gold contacts of PCB during wave soldering and the hot air leveling process. It is also designed for insulating coil at high temperatures as well as for products like generators, capacitors, and transformes. volzElektro 1018 PV4 has UL-registration under # E338128.

Nominal Values

Backing Kapton®, CR (Corona resitant), Polyimide Film

Backing Thickness 0,025 mm

> **Adhesive Type** Silicone, thermosetting

Total Thickness 0,064 mm

Insulation Class N 200°C (DIN EN 60085 & OANZ2), C (OANZ8)

> Color Amber (00)

Adhesion to Steel 5.90 N/25 mm

Tensile Strength 137,00 N/25 mm

Elongation at Break 80%

Dielectric Strength 7000 V

-73°C to +260°C **Temperature Resistance**

> **UL-File #** E338128

Length 33 m, other lengths upon request

6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 495 Width

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 08 April 2024





DE-79227 Schallstadt



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of











Technical Product Data Sheet

volzElektro 1018 PV4



Applications

- Veneering for high temperatures
- Bundling and fixing of components (thermal switches) exposed to high temperatures
- Electrical insulation of coils, transformers, conductors, and cables for class N applications (200°C)
- Veneering of PCB gold contacts and protection of plug contacts and switches during soldering

Benefits

- Good resistance to most alcohols, esters, ketones and oils
- Clean, residue-free removal in one piece after exposure to high temperatures
- High-strength backing provides superior puncture, tear and abrasion resistance
- Chemical resistant
- Excellent thin electrical insulation
- Flame retardant
- Temperature resistance: 200°C continuous thermal class N.

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 02.07.2025













DE-79227 Schallstadt