

volzElektro 1019



volzElektro 1019 has a commercial grade polyimide film with high-performance, thermosetting silicone adhesive. volzElektro 1019 can protect gold contacts of PCB during wave soldering and hot air leveling processes. It is also designed for insulating coil at high temperatures as well as for generators, capacitors and transformers. volzElektro 1019 has UL-registration under E338128.

Nominal Values

Backing	Polyimide Film
Backing Thickness	0,050 mm
Adhesive Type	Silicone, thermosetting
Total Thickness	0,090 mm
Insulation Class	N 200°C (DIN EN 60085 & OANZ2), C (OANZ8)
Color	Amber (00)
Adhesion to Steel	7,00 N/25 mm
Tensile Strength	255,00 N/25 mm
Elongation at Break	60%
Dielectric Strength	6500 V
UL-File #	E338128
Length	33 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 635 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	15 February 2021

volzElektro 1019



Applications

- On gold fingers for protection in wave soldering
- Ground barrier and phase insulation in high performance torroidal coils
- Outer wrap on small bobbin wound coils and Form wound coils for traction motors
- Core and inter-layer insulation in transformers
- Final bandaging of coils
- Taping of coreless coils
- Contact protection against current carrying conductors
- Splicing of Films and Foils

Benefits

- Excellent mechanical and electrical properties
- High conformability
- Good adhesive properties, excellent holding and packaging properties

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 22.07.2025