

## volzElektro 11600 PV3



volzElektro 11600 PV3 consists of a PET Cloth with a tear-resistant carrier and a highly-efficient, thermosetting acrylic adhesive. It is easy to process, conformable, has a high tensile strength, and is extremely resistant to chemicals. It is oil resistant to Ninas 10 vetro GBN. Resistance to other oils should be tested individually.

## Nominal Values

<b>Backing</b>	PET Cloth
<b>Backing Thickness</b>	0,125 mm
<b>Adhesive Type</b>	Acrylic, thermosetting
<b>Total Thickness</b>	0,180 mm
<b>Insulation Class</b>	B 130°C (DIN EN 60085, OANZ2 & OANZ8)
<b>Color</b>	White (08), Black (04)
<b>Adhesion to Steel</b>	11,80 N/25 mm
<b>Tensile Strength</b>	314,00 N/25 mm
<b>Elongation at Break</b>	12%
<b>Dielectric Strength</b>	2000 V
<b>Temperature Resistance</b>	-30°C to +175°C
<b>Length</b>	33 m, 50 m, other lengths upon request
<b>Width</b>	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 800 mm, other widths upon request
<b>Storage Life</b>	The material can be stored at room temperature for at least 12 months.
<b>Effective</b>	05 December 2019

## volzElektro 11600 PV3



### Applications

- Strain relief for supply lines
- Closing bandage
- Masking of self-supporting coils
- protection for resin treatment
- Masking for multiple coil winding
- Fastening of non-sticking insulation
- Spiral head and phasing insulation
- Wrapping outer coils

### Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 13.09.2025