

## volzElektro 41356 PV4



volzElektro 41356 PV4 is a PET film/Nomex® laminate coated on one side with a thermosetting rubber adhesive. Developed for high-temperature electrical applications requiring a thin, puncture-resistant carrier.

### Nominal Values

<b>Backing</b>	PET Laminate, PET Fim / Nomex®
<b>Backing Thickness</b>	0,090 mm
<b>Adhesive Type</b>	Natural Rubber, thermosetting
<b>Total Thickness</b>	0,135 mm
<b>Insulation Class</b>	F 155°C (DIN EN 60085, OANZ2 & OANZ8)
<b>Color</b>	White (08)
<b>Adhesion to Steel</b>	13,75 N/25 mm
<b>Tensile Strength</b>	162,50 N/25 mm
<b>Elongation at Break</b>	10%
<b>Dielectric Strength</b>	7000 V
<b>Electrolytic Corrosion</b>	1
<b>Rolling Ball Tack</b>	< 10 cm
<b>Temperature Resistance</b>	#BEZUG!
<b>Length</b>	50 m, other lengths upon request
<b>Width</b>	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 914 mm, other widths upon request
<b>Storage Life</b>	The material can be stored at room temperature for at least 12 months.
<b>Effective</b>	18 November 2025

## volzElektro 41356 PV4



### Applications

- Phase insulation of electrical motors, generators, etc.
- Outer wrapping, tabbing and anchoring leads of electrical transformers, coils, etc

### Benefits

- Very good thermal resistance and outstanding breakdown voltage
- High initial adhesion
- Good chemical resistance when thermoset

### Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 29.01.2026