

Technical Product Data Sheet

volzElektro 50501 PV1



volzElektro 50501 PV1 is a 23 micron polyester film coated with high quality acrylic adhesive. Designed for coil wrapping, inter-layer insulation, anchoring, holding, harnessing, splicing, etc. Excellent flagging and solvent resistance.

Nominal Values

Backing PET Film

Backing Thickness 0,023 mm

Adhesive Type Acrylic

Total Thickness 0,060 mm

Color Clear (00), Yellow (17), Red (19), Blue (11), Black (04), Green (37), White (08)

Adhesion to Steel 6,25 N/25 mm

Tensile Strength 100,00 N/25 mm

Elongation at Break 80%

Dielectric Strength 4500 V

Electrolytic Corrosion A1,0

Rolling Ball Tack < 10 cm

Temperature Resistance +180°C, (short-term)

Length 66 m, other lengths and spools upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1280

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 20 May 2022















DE-79227 Schallstadt



Technical Product Data Sheet

volzElektro 50501 PV1



Applications

- Coil wrapping
- Anchoring
- Harnessing
- Holding
- Tabbing and inter-layer insulation
- Splicing of papers and films

Benefits

- Good adhesion and initial tack
- High conformability and chemical resistance
- Motor and transformer manufacturers

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 16.09.2025













