

volzElektro 54354



volzElektro 54354 is a electrical tape manufactured of a combination of a polyesterfilm and a special paper, laminated with a thermosetting rubber adhesive. This combination gives high strength and very good insulating properties. volzElektro 54354 is very good on uneven surfaces. It is resistant against varnish and other chemicals.

Nominal Values

| | |
|--------------------------------------|---|
| Backing | PET Laminate, PET Film / Paper |
| Backing Thickness | 0,160 mm |
| Adhesive Type | Natural Rubber, thermosetting |
| Total Thickness | 0,220 mm |
| Insulation Class | B 130°C (DIN EN 60085, OANZ2 & OANZ8) |
| Color | Beige (24) |
| Adhesion to Steel | 16,25 N/25 mm |
| Tensile Strength | 175,00 N/25 mm |
| Elongation at Break | 20% |
| Dielectric Strength | 8000 V |
| Insulation Resistance (megaΩ) | 5*10 ⁶ Ω |
| Electrolytic Corrosion | B3,0 |
| Flammability | BU2 |
| Temperature Resistance | +160°C, (short-term) |
| Length | 50 m, Other lengths upon request |
| Width | 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1210 mm, other widths upon request |
| Storage Life | The material can be stored at room temperature for at least 12 months. |
| Effective | 20 March 2026 |

volzElektro 54354



Applications

- Holding and insulation applications during transformer and motor manufacturing
- Ground and barrier insulation for electrical motors, generators, etc.
- Outer wrapping, tabbing, harnessing and anchoring leads for electrical transformers, coils, etc.

Benefits

- Excellent electrical properties and thermal resistance
- Puncture resistance
- Excellent solvents and chemical resistance when thermoset
- Ground and barrier insulation for electrical motors, generators, etc.
- Outer wrapping, tabbing, harnessing and Anchoring leads for electrical transformers, coils, etc.

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 15.04.2026