


Technical Product Data Sheet

volzElektro 6017 PV3



Nominal Values

Glass Cloth **Backing**

Backing Thickness 0,140 mm

> **Adhesive Type** Acrylic, thermosetting

Total Thickness 0,190 mm

Insulation Class F 155°C (DIN EN 60085, OANZ2 & OANZ8)

> Color White (08)

Adhesion to Steel 11,10 N/25 mm

Tensile Strength 637,00 N/25 mm

Elongation at Break 15%

Dielectric Strength 3000 V

> **UL-File #** E338128

Length 55 m, other lengths upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1075

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 21 January 2020





DE-79227 Schallstadt



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of









Technical Product Data Sheet

volzElektro 6017 PV3



Applications

- Inter-layer insulation
- Coil outer wraps
- Tie-downs
- Lead insulation and protection
- Electrical motor and generator binding

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15° C to 24° C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15° C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 26.11.2025







We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the







