

Technical Product Data Sheet

volzElektro 6215 PV3

volzElektro 6215 PV3 is a 2 mils polyester (PET) film with 1,20 mil highly efficient, silicone adhesive. This product was designed to provide high tack and adhesion, and has a strong resistance to corrosive chemicals. It can be easily removed from applied surface without adhesive residue, making it an excellent tape for masking applications and to be used for powder coating.

Nominal Values

Backing PET Film

Backing Thickness 0,050 mm

Adhesive Type | Silicone

Total Thickness 0,080 mm

Insulation Class B 130°C (DIN EN 60085, OANZ2 & OANZ8)

Color Green (37)

Adhesion to Steel (N/25mm) 9,30 N/25 mm

Tensile Strength 221,00 N/25 mm

Elongation at Break 135%

Breakdown Voltage (Veff VDE 0303) 8000 V

Length 66 m, other lengths upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 975

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 17 January 2024















DE-79227 Schallstadt



Technical Product Data Sheet

volzElektro 6215 PV3

Applications

- Excellent masking tape
- Intended for high temperature masking in powder coatings

Benefits

- Applicable up to 225°C
- High Tack and adhesion offering masking protection
- Residue-free removal
- Tear and Break resistance
- Excellent resistance to corrosive chemicals

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 17.04.2024







We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the







standard processing guidelines for adhesive tapes, which we will gladly send you upon request.