volzFix 9065 PV1



volzFix 9065-PV1 is a double-sided polyester adhesive tape with a modified solvent acrylate adhesive compound. It is characterized by very good adhesive strength and very high heat resistance and is also suitable for difficult applications. The tape has good UV resistance and is well compatible with other materials.

Nominal Values

Backing	PET Film
Backing Thickness	0,012 mm
Adhesive Type	modified, Solvent Acrylic
Total Thickness	0,205 mm, ± 10%
Color	Clear (00)
Liner	120 g, white, PE Paper
Adhesion to Steel	≥ 20,00 N/25 mm, FINAT1, ASTM3121-94
Shear Strength	≥ 168 h
Temperature Resistance	-40°C to +100°C, -40°C to +150°C (short-term), -20°C to +80°C (long-term)
Length	50 m, 100 m, 500 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1240 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Additional Info	Adhesive application 205g/sqm
Effective	09 April 2024

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

volzFix 9065 PV1



Applications

- Very good application on high and low energy plastics
- Widely used in membrane switch and electrical industry (e.g. smartphones)
- LCD technology

Benefits

- Very high initial tack and adhesion
- Good UV resistance
- High temperature resistance
- Very good die-cutting properties

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 23.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com