volzFix 9065

volzFix 9065 is a double-sided, PET Film with a modified-solvent acrylic. The tape has a very high initial tack, superior adhesion, and outstanding holding power. It is also has excellent resistance against environmental influences, e.g. light, heat and humidity.

Nominal Values

Backing	PET Film
Backing Thickness	0,012 mm
Adhesive Type	modified, Solvent Acrylic
Total Thickness	0,205 mm
Color	Clear (00)
Liner	red, MOPP Film
Adhesion to Steel (N/25mm)	≥ 20,00 N/25 mm
Shear Strength	≥ 168 h
Rolling Ball Tack	≥ 1 cm
Temperature Resistance	-40°C to +100°C, -40°C to +180°C (short-term)
Length	50 m, 100 m, 500 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1240 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	9 March 2021

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

volzFix 9065

Applications

- Assembly of ABS parts in the automotive industry
- Self-adhesive finishing of rubber and EPDM
- Strip bonding in the furniture industry
- Sealing of insulation pipe shells
- Display (e.g. mobile phones) and sign bonding
- Equipping lead profiles with self-adhesive
- Convertible automobile top bonding
- Seamless gluing of aluminum sheets
- Roof liner adhesion

Benefits

- Very high initial tack
- Superior adhesion and outstanding holding power
- Excellent resistance against environmental influences, e.g. light, heat and humidity
- Good die-cutting properties

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 20.04.2024

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com