

## **Technical Product Data Sheet**

## volzFix 9065



volzFix 9065 is a double-sided, PET Film with a modified-solvent acrylic. The tape has a very high initial tack, superior adhesion, and outstanding holding power. It is also has excellent resistance against environmental influences, e.g. light, heat and humidity.

### **Nominal Values**

Manufacturer | VOLZ®

**Backing** PET Film

**Backing Thickness** 0,012 mm

**Adhesive Type** | modified, Solvent Acrylic

**Total Thickness** 0,205 mm

**Color** Clear (00)

**Liner** Red, MOPP Film

**Adhesion to Steel** ≥ 20,00 N/25 mm

**Shear Strength** ≥ 168 h

**Rolling Ball Tack** ≥ 1 cm

**Temperature Resistance** 40°C to +100°C, -40°C to +180°C (short-term)

**Length** 50 m, 100 m, 500 m, other lengths upon request

**Width** 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1240

mm, other widths upon request

**Storage Life** The material can be stored at room temperature for at least 12 months.

**Effective** 09 March 2021





DE-79227 Schallstadt



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of











# **Technical Product Data Sheet**

## volzFix 9065



### **Applications**

- Assembly of ABS parts in the automotive industry
- Self-adhesive finishing of rubber and EPDM
- Strip bonding in the furniture industry
- Sealing of insulation pipe shells
- Display (e.g. mobile phones) and sign bonding
- Equipping lead profiles with self-adhesive
- Convertible automobile top bonding
- Seamless gluing of aluminum sheets
- Roof liner adhesion

#### **Benefits**

- Very high initial tack
- Superior adhesion and outstanding holding power
- Excellent resistance against environmental influences, e.g. light, heat and humidity
- Good die-cutting properties

#### **Storage Conditions**

The Rolls should be stored in their packaging protected from light and at a temperature between  $15^{\circ}$ C to  $24^{\circ}$ C, with a relative humidity of 50% + /- 30%. When using an adhesive tape stored below  $15^{\circ}$ C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 21.11.2024













DE-79227 Schallstadt