

Technical Product Data Sheet

volzFix 9065



volzFix 9065 is a double-sided, PET Film with a modified-solvent acrylic. The tape has a very high initial tack, superior adhesion, and outstanding holding power. It is also has excellent resistance against environmental influences, e.g. light, heat and humidity.

Nominal Values

Backing PET Film

Backing Thickness 0,012 mm

Adhesive Type | modified, Solvent Acrylic

Total Thickness 0,205 mm

Color Clear (00)

Liner Red, MOPP Film

Adhesion to Steel ≥ 20,00 N/25 mm

Shear Strength ≥ 168 h

Rolling Ball Tack ≥ 1 cm

Temperature Resistance 40°C to +100°C, -40°C to +180°C (short-term)

Length 50 m, 100 m, 500 m, other lengths upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1240

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 09 March 2021





DE-79227 Schallstadt



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the











Technical Product Data Sheet

volzFix 9065



Applications

- Assembly of ABS parts in the automotive industry
- Self-adhesive finishing of rubber and EPDM
- Strip bonding in the furniture industry
- Sealing of insulation pipe shells
- Display (e.g. mobile phones) and sign bonding
- Equipping lead profiles with self-adhesive
- Convertible automobile top bonding
- Seamless gluing of aluminum sheets
- Roof liner adhesion

Benefits


- Very high initial tack
- Superior adhesion and outstanding holding power
- Excellent resistance against environmental influences, e.g. light, heat and humidity
- Good die-cutting properties

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 15.09.2025













DE-79227 Schallstadt