volzFix 9067 PV6

volzFix 9067 PV6 is a double-sided, polyester film adhesive tape with a modified solvent acrylic adhesive. It has very good initial tack, very good adhesion, and holding power. volzFix 9067 PV6 has excellent resistance against environmental factors such as light, heat and humidity.

Nominal Values

Backing	PET Film
Backing Thickness	0,012 mm
Adhesive Type	modified, Solvent Acrylic
Total Thickness	0,160 mm
Color	Clear (00)
Liner	red, MOPP Film
Adhesion to Steel	≥ 18,75 N/25 mm
Shear Strength	≥ 100 h
Temperature Resistance	-20°C to +100°C
Length	50 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1240 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	28 January 2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

volzFix 9067 PV6

Applications

- Widely used in the membrane switch and electrical industry (e.g. smart phones)
- Modular construction
- Fixation of microphone gauze, LCD reflective film, etc.

Benefits

- Great inital tack
- Very good adhesion and holding power
- Excellent resistance against environmental factors such as light, heat and humidity
- Secure bonding to high energy surface substrates
- Good die-cut processability

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 23°C to 28°C, with a relative humidity of 50%. When using an adhesive tape stored below 23°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 22.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com