

# **Technical Product Data Sheet**

## volzFix 9080-105



volzFix 9080-105 is a double-sided adhesive tape consisting of a PET-carrier coated with a modified-solvent acrylic. The tape is Covered on both sides with a 105g white paper liner. It is characterized by very good adhesion and high temperature resistance, suitable for difficult applications. The tape has a good UV resistance and is compatible with other materials.

### **Nominal Values**

**Backing** PET Film

**Backing Thickness** 0,012 mm

**Adhesive Type** modified, Solvent Acrylic

**Total Thickness** 0,080 mm

Color Clear (00)

**Liner** 105 g, white, PE Paper

Adhesion to Steel ≥ 15,00 N/25 mm, FINAT 1 & ASTM/D3330M-04

**Loop Tack** ≥ 14,00 N/25 mm, FINAT 9

Shear Strength ≥ 168 h, FINAT-8 & ASTM/D3654M-02

**Rolling Ball Tack** ≥ 4 cm, ASTM3121-94

**Temperature Resistance** -20°C to +80°C, -40°C to +120°C (short-term)

**Length** 50 m, 100 m, 500 m, other lengths upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1240

mm, other widths upon request

**Storage Life** The material can be stored at room temperature for at least 12 months.

**Effective** 21 February 2022













DE-79227 Schallstadt



# **Technical Product Data Sheet**

## volzFix 9080-105



### **Applications**

- Application where thinness and high transparency are required
- Widely applied in membrane switch industries and electronic industries, e.g. mobile phone modular assembly, LCD cushion and reflective film fixation, etc.

#### **Benefits**

- Very thin and transparent, with good adhesion
- Good resistant to moisture, which can work under a wet environment
- Allow secure bonding to high energy surface substrates
- Short-term holding of weight is possible

#### **Storage Conditions**

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 10.04.2025











