

## volzFix V4140 PV1



volzFix V4140 PV1 is a double-sided, self-adhesive tape produced of a clear, BOPP-film carrier and a clear, hot-melt, synthetic-rubber adhesive. The product is perfect for carpet laying or bonding of metal and plastics where no high temperatures is needed. The product also has a very high tack.

### Nominal Values

|                               |   |
|-------------------------------|---|
| <b>Backing</b>                | BOPP Film, Clear  |
| <b>Backing Thickness</b>      | 0,060 mm  |
| <b>Adhesive Type</b>          | Synthetic Rubber, Clear   |
| <b>Total Thickness</b>        | 0,095 mm  |
| <b>Color</b>                  | Clear (00)  |
| <b>Liner</b>                  | 65 g, yellow, bi-siliconized, Paper   |
| <b>Adhesion to Steel</b>      | 20,00 N/25 mm   |
| <b>Tensile Strength</b>       | 105,00 N/25 mm  |
| <b>Elongation at Break</b>    | > 150%  |
| <b>Shear Strength</b>         | > 27 h  |
| <b>Rolling Ball Tack</b>      | 5 cm, + 2 cm  |
| <b>Temperature Resistance</b> | -10°C to +50°C  |
| <b>Length</b>                 | 25 m, 50 m, 100 m, 1000 m, 2600 m, other lengths upon request                                   |
| <b>Width</b>                  | 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1500 mm, other widths upon request |
| <b>Storage Life</b>           | The material can be stored at room temperature for at least 12 months.                          |
| <b>Effective</b>              | 05 March 2021   |

## volzFix V4140 PV1



### Applications

- General purpose tape
- Bonding of foils, cardboards, posters and more
- Carpet laying tape

### Benefits

- Excellent tack
- Good adhesion
- Good conformability onto different surfaces
- Hand tearable
- Flexible carrier

### Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 19°C to 21°C, with a relative humidity of 50%. When using an adhesive tape stored below 19°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 30.01.2026