volzFix V5263 PV2



volz5263 PV2 is a double-sided adhesive film without a carrier and with a modified dispersion acrylic adhesive. It is characterized by high temperature and aging resistance, as well as high peel adhesion with extensive plasticizer resistance.

Nominal Values

Backing	Transfer
Adhesive Type	modified, Dispersion Acrylic
Total Thickness	0,050 mm
Color	Clear (00)
Liner	yellow, bi-siliconized, Paper
Adhesion to Steel	12,00 N/25 mm
Loop Tack	13,00 N/25 mm
Shear Strength	> 24 h
Temperature Resistance	-40°C to +140°C
Length	50 m, 500 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1000 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	09 August 2021

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

volzFix V5263 PV2



Applications

- Commercial and industrial finishing of textiles, wood, soft PVC and smooth to slightly textured surfaces

Benefits

- High temperature and aging resistance
- Largely plasticizer resistant
- High peel adhesion

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 22.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com