volzFix V5265-PE



volzFix V5265 PE is a 125 micron, modified acrylic adhesive wound on a brown siliconized paper release liner. Designed for mounting various materials as fabrics, paper, plastic films, metal foils, cardboard, glass, etc. It has a very high tack and adhesion, with good shear strength and ageing resistance.

Nominal Values

Backing	Transfer
Adhesive Type	modified, Solvent Acrylic
Total Thickness	0,125 mm
Color	Clear (00)
Liner	brown, bi-siliconized, Paper
Adhesion to Steel	22,50 N/25 mm
Shear Strength	168 h
Rolling Ball Tack	< 10 cm
Temperature Resistance	-30°C to +110°C, +140°C (short-term)
Length	50 m, other lengths upon request
Width	6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1500 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	17 October 2025

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

volzFix V5265-PE



Applications

- Paper and plastic industry, flying splices, core starting, end-tabbing, packaging, etc.
- Laminations of fabrics and foam, mounting of displays, photo, posters, leaflets, etc.

Benefits

- Very high tack and adhesion
- Good shear strength and ageing resistance
- Acid free

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 22.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com