

Technical Product Data Sheet

volzFix V9067



volzFix 9067 is a double-sided adhesive tape with polyester-film carrier and a modified-solvent acrylic adhesive. Suitalbe for applications where a thin and highly transparent tape is required.

Nominal Values

PET Film **Backing**

Backing Thickness 0,012 mm

> **Adhesive Type** modified, Solvent Acrylic

Total Thickness 0,160 mm

> Color Clear (00)

Liner 90 g/m², brown, siliconized Paper

Adhesion to Steel 18,00 N/25 mm

> **Loop Tack** 28,00 N/25 mm

Shear Strength > 400 h

Temperature Resistance -40°C to +160°C, +180°C (short-term)

> Length 50 m, 500 m, other lengths upon request


6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1000 Width

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 11 August 2021





DE-79227 Schallstadt



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of











Technical Product Data Sheet

volzFix V9067



Applications

- Widely used in the membrane switch and electrical industry (e.g. smart phones)
- Modular construction
- Production of corrugated cardboard and paper, and treated cardboard, paper foils, and metal plates
- Mounting and lamination of various insulating and foamed materials
- Applications where high transparency is required
- Good for foam lamination

Benefits

- Good tack, very good UV ageing resistance, very good humidity resistance
- Good resistance to chemicals, good softener resistance
- Very aggressive adhesive with high adhesive strength even at high and low temperatures
- Very good converting performance because of a stable PET carrier and reduced adhesive mass flow

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15° C to 24° C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15° C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 13.12.2025















DE-79227 Schallstadt