volzMasking 3016U

volzMasking 3016U is a masking tape suitable for curing at 80°C (1 hour) in automotive repair shops, especially car body shops.

Nominal Values

Backing	Saturated Crepe Paper
Backing Thickness	0,090 mm
Adhesive Type	Natural rubber and Hydrocarbon Resins
Total Thickness	0,132 mm
Color	Ivory (00), other colors upon request
Adhesion to Steel	6,75 N/25 mm
Tensile Strength	85,00 N/25 mm
Elongation at Break	10%
Temperature Resistance	+80°C (1 h)
Length	50 m, other lengths upon request
Width	19 mm, 25 mm, 50 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	24 March 2025

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

volzMasking 3016U

Applications

- Masking tape for the automotive industry

Benefits

- Excellent adhesion to all surfaces
- Easy application on curved profiles and irregular surfaces
- Easy removal without adhesive residue
- Heat resistant up to 80°C (1 hour)
- Compatible with solvent-based and most water-based paints

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 23.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com