volzMount 9050P



volzMount 9050P is part of a pressure-sensitive, fastening system consisting of a variety of cross-linked, closed-cell, PE Foams and a specific formulated adhesive. It is available in various thickness, density, and colors.

Nominal Values

Backing	PE Foam
Backing Thickness	0,800 mm
Adhesive Type	Natural Rubber
Total Thickness	0,900 mm
Color	Black (04)
Liner	90 g, white, siliconized Paper
Adhesion to Steel	> 15,00 N/25 mm
Tensile Strength	> 26,60 N/25 mm
Elongation at Break	500%
Shear Strength	> 5000 h
Temperature Resistance	-40°C to +60°C
Length	16,5 m, other lengths upon request
Width	1500 mm, other widths upon request
Storage Life	The material can be stored at room temperature for at least 12 months.
Effective	02 March 2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com

volzMount 9050P



Applications

- For mounting of knobs, handles, windows bars, etc.
- Fixing lettering and badges in automotive industry

Benefits

- Very high peel and shear properties
- Resistant to water, detergents and alcohol
- IMDS – automotive registration

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 19°C to 21°C, with a relative humidity of 50%. When using an adhesive tape stored below 19°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 05.11.2026

We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the standard processing guidelines for adhesive tapes, which we will gladly send you upon request.

Volz Selbstklebetecknik GmbH
Fischerinsel 3
DE-79227 Schallstadt
Phone: +49 (0)7664 50500-0
Fax: +49 (0)7664 50500-50
info@volztapes.com
www.volztapes.com