

Technical Product Data Sheet

volzMount V4300 PV1



volzMount V4300 PV1 is a double-sided, self-adhesive tape with a 75 kg/m³, closed-cell, PE-foam carrier and a white, synthetic-rubber adhesive. It has a very aggressive adhesive, high tack, good cohesion, and a high holding power at high and low temperatures.

Nominal Values

Backing PE Foam, closed-cell, White, 75 kg/m³

Adhesive Type Synthetic Rubber, Clear

Total Thickness 1,050 mm

> Color White (08)

Liner 80 g, yellow, bi-siliconized, Paper

Adhesion to Steel > 14,00 N/25 mm

Tensile Strength > 31,00 N/25 mm

Elongation at Break > 190%

> **Shear Strength** > 2 h

Rolling Ball Tack < 1,5 cm

Temperature Resistance -10°C to +60°C

> Length 5 m, 33 m, 66 m, 350 m, other lengths upon request

6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1400 Width

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 17 June 2021







We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the









DE-79227 Schallstadt



Technical Product Data Sheet

volzMount V4300 PV1



Applications

- Bonding of profiles, frames, nameplates, plastics, emblems
- Suitable for all vertical applications in particular fixing of accessories
- Suitable for permanent fixing of glass and mirrors

Benefits

- Adhesive with good adhesion, high tack and good cohesion even at low and high temperatures
- Resistant to weathering and chemicals
- Good UV resistance
- Very high bond on low surfaces energy substrates

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 19°C to 21°C, with a relative humidity of 50%. When using an adhesive tape stored below 19°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 30.11.2025











