

Technical Product Data Sheet

volzMount V5341



volzMount V5341 is a double sided self-adhesive tape with a 3mm closed cell, low density white PE foam carrier coated with a high performance rubber adhesive system and protected by siliconized paper release liner. Designed for general purpose mounting, assembling of displays, hooks, cable clips, plastic profiles, poster, etc. High thickness, ideal for applications on rough and irregular surfaces.

Nominal Values

Backing PE Foam

Backing Thickness 3,000 mm

Adhesive Type | Synthetic Rubber

Total Thickness 3,100 mm

Color White (08)

Liner bi-siliconized, Paper

Adhesion to Steel 10,00 N/25 mm, (90°)

Shear Strength ≥ 168 h

Rolling Ball Tack < 10 cm

Temperature Resistance -10°C bis +70°C, -10°C bis +100°C (short-term)

Length 16,5 m, other lengths upon request

Width 6 mm, 9 mm, 12 mm, 15 mm, 19 mm, 25 mm, 30 mm, 38 mm, 50 mm, 1500

mm, other widths upon request

Storage Life The material can be stored at room temperature for at least 12 months.

Effective 24 March 2022





DE-79227 Schallstadt



We provide the technical data of our products to the best of our knowledge, but without obligation. Due to the wide range of material and environmental influences, we recommend a suitability test on original products prior to use. Please also note the











Technical Product Data Sheet

volzMount V5341



Applications

- Mounting of plastic parts in automotive and home appliance industry
- Mounting of decorative profiles, furniture trims, electrical conduits
- Mounting of nameplates, emblems and plastic profiles in the building and construction industry

Benefits

- High initial tack
- Good adhesion to a variety of smooth and rough substrates
- Good ageing resistance

Storage Conditions

The Rolls should be stored in their packaging protected from light and at a temperature between 15°C to 24°C, with a relative humidity of 50% +/- 30%. When using an adhesive tape stored below 15°C, it is advisable to keep the tape at room temperature for 24 hours to preserve its characteristics.

Print Date: 30.07.2025











